

# PRODUCT DATA SHEET

## Sikalastic®-701

Polyurethane hybrid elastic top coat for liquid applied membrane waterproofing systems

### DESCRIPTION

Sikalastic®-701 is a 2-part, polyurethane hybrid, gloss finish top coat for Sika® Liquid Applied Membrane waterproofing systems.

Sikalastic®-701 is commonly used in conjunction with SikaRoof® MTC-UV systems and can also be used with Sikalastic® polyurea systems.

### USES

Sikalastic®-701 may only be used by experienced professionals.

A gloss finish top coat for:

- Sika® Liquid Applied Membrane systems
- Sika® 2-C spray applied PU/PUA systems

For the following waterproofing system applications:

- Newly applied or renovating existing membranes
- Flat and pitched roof structures
- Communal walkways
- Podium decks
- Terrace roofs
- For exterior use only

### CHARACTERISTICS / ADVANTAGES

- Aliphatic polyurethane providing UV and yellowing resistance
- Good long term weathering performance
- Good colour stability and gloss retention
- Good chemical resistance
- Low soiling and easily cleanable
- Suitable for cool roofs by providing a high Solar Reflective Index
- Resistant to ponding water

### APPROVALS / CERTIFICATES

- CE Marking and Declaration of Performance to European Technical Assessment ETA-20/0248, based on ETAG 005 Part 1 and Part 6 — Liquid applied roof waterproofing kits. Part 1: General. Part 6: Specific stipulations for Kits based on Polyurethane
- Fire Testing EN 13501-1, Sikalastic®-701, Sikalastic®-702, warringtonfire, Report No.19896B
- Abrasion resistance AR0.5(Special), Sikalastic®-701, Sikalastic®-702, FACE, Test report No. FC/18/8048
- AS4654.1:2012 Waterproofing membranes for external above-ground use (BRANZ)

### PRODUCT INFORMATION

<b>Composition</b>	Elastomeric Polyurethane/Hybrid	
<b>Packaging</b>	Part A	10kg container
	Part B	2.5kg container
	Part A + B	12.5kg ready to mix unit
<b>Shelf life</b>	24 months from date of production	
<b>Storage conditions</b>	Store properly in original, unopened and undamaged packaging, in dry conditions at temperatures between +5 °C and +30 °C. Always refer to packaging.	
<b>Colour</b>	Light Grey (RAL 7035)	
	White (RAL 9016)	

Density	~1.25 kg/l (mixed A+B) Value at +23 °C		(DIN EN ISO 2811-11)
Solid content by mass	Part A	~67 %	
	Part B	~100 %	
Solid content by volume	Part A	~55 %	
	Part B	~100 %	

## TECHNICAL INFORMATION

Tensile strength	<b>Temperature</b>	<b>Value</b>	(EN ISO 527-3)
	+23 °C	~10 MPa	
	-20 °C	~20 MPa	
Tensile strain at break	<b>Temperature</b>	<b>Value</b>	(EN ISO 527-3)
	+23 °C	~100 %	
	-20 °C	~20 %	
Solar reflectance	Initial Solar Reflectance	0,88	(ASTM C1549)
Thermal emittance	Initial Thermal Emittance	0,86	(ASTM C1371)
Solar reflectance index	Initial SRI (Convective Coefficient, Medium Wind)	~112	
Chemical resistance	Resistant to many chemicals. Contact Sika Technical Service for additional information.		
External fire performance	Broof T1 / Broof T4		(prEN 1187)
Reaction to fire	Euroclass E		(EN 13501-1)

## SYSTEM INFORMATION

System structure	<p>Sikalastic®-701 can be used with the following:</p> <p><b>1-Part PU cold applied Systems</b></p> <ul style="list-style-type: none"> <li>▪ Sikalastic®-488/SL</li> <li>▪ Sikalastic®-888</li> </ul> <p><b>2-Part PU/PUA hot spray applied Systems</b></p> <ul style="list-style-type: none"> <li>▪ Sikalastic®-851 R</li> <li>▪ Sikalastic®-888</li> <li>▪ Sikalastic®-888 Hybrid</li> </ul> <p>Refer to the following System Data Sheets:</p> <ul style="list-style-type: none"> <li>▪ SikaRoof® MTC- UV</li> </ul>
------------------	--

Dry film thickness	<b>Dry film thickness (DFT):</b> 220 micron
--------------------	---

## APPLICATION INFORMATION

Mixing ratio	Part A : Part B = 80 : 20 (by volume)	
Consumption	<b>Wet film thickness (WFT):</b> 280 micron Approximately 35m <sup>2</sup> per 12.5kg pail	
Yield	~0.35 kg/m <sup>2</sup> applied in a single coat	
Ambient air temperature	+2 °C min. / +40 °C max.	
Relative air humidity	Above +20 °C	35 % min / 80 % max.
	Below +20 °C	45 % min. / 80 % max.

<b>Dew point</b>	Beware of condensation. The substrate and uncured applied membrane must be at least +3 °C above dew point to reduce the risk of condensation or blooming on the membrane finish.					
<b>Substrate temperature</b>	+2 °C min. / +40 °C max.					
<b>Substrate moisture content</b>	Refer to Product Data Sheet of the appropriate base layers					
<b>Pot Life</b>	1 hour at +20 °C Pot life will decrease at higher temperatures and increase at lower temperatures.					
<b>Tack free time</b>	<b>Condition</b>	<b>Property</b>	<b>Value</b>	(EN 29117:1992)		
	20 °C / 50 % RH	Tack free time	~45 minutes			
	20 °C / 50 % RH	Hard drying time	~60 minutes			
	20 °C / 50 % RH	Final drying time	~90 minutes			
	<b>Condition</b>	<b>Property</b>	<b>Value</b>	(EN 29117:1992)		
	5 °C / 50 % RH	Tack free time	~75 minutes			
	5 °C / 50 % RH	Hard drying time	~105 minutes			
	5 °C / 50 % RH	Final drying time	~135 minutes			
	Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.					
	<b>Applied product ready for use</b>	<b>Temperature</b>	<b>Relative Humidity</b>	<b>Rain Resistant</b>	<b>Foot Traffic</b>	<b>Full Cure</b>
+10 °C		50 %	~75 minutes	~150 minutes	~1 day	
+20 °C		50 %	~60 minutes	~120 minutes	~1 day	
+30 °C		50 %	~45 minutes	~90 minutes	~16 hours	
Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.						

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## FURTHER INFORMATION

- Safety Data Sheet (SDS)
- Sika Method Statement: SikaRoof® MTC-UV systems

## IMPORTANT CONSIDERATIONS

Installation work must only be carried out by Sika® trained and approved contractors, experienced in this type of application.

- Products must only be applied in accordance with their intended use.
- Do not use for indoor applications.
- Do not apply near to running air intakes of air conditioning units. Switch off units before applying.
- Do not dilute with any solvent or water.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

### SUBSTRATE PREPARATION

Confirm waiting /overcoating time has been achieved on the previously applied system base layer. The base layer must be clean, dry and free of all contaminants such as dirt, oil, grease, coatings and loose material. If dust exists on the surface, it must be completely removed before application of the product, preferably by vacuum extraction equipment.

If the maximum overcoating time of the base layer is exceeded, the surface must be lightly abraded using light abrasive manual tools or mechanical equipment to roughen the surface. Depending on the type of base layer, a solvent wipe may also be required. Finally, completely remove all the dust by vacuum extraction equipment.

### MIXING

Prior to mixing all parts, mix separately Part A (resin) using an electric single or double paddle mixer and stirrer (300 to 400 rpm) or other suitable equipment. Mix liquid and all the coloured pigment until a uniform colour / mix has been achieved. Add Part B (hardener) to Part A and mix Part A + B continuously for 3,0 minutes until a uniformly coloured mix has been achieved. Mix full units only. Mixing time for A+B = ~3,0 minutes.

## APPLICATION

Apply mixed product in 1 coat by roller, brush or spray equipment to achieve a consistent thickness and required surface finish.

## CLEANING OF EQUIPMENT

Clean all tools and application equipment with water immediately after use. Hardened material can only be removed mechanically or with a proprietary paint stripper.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### Sika Australia Pty Limited

ABN 12 001 342 329

aus.sika.com

Tel: 1300 22 33 48

### Product Data Sheet

Sikalastic®-701

April 2023, Version 01.03

020915505000000013